

**INTERNATIONAL STANDARD GUIDE****Glazing of Artworks and Keepsakes**GLZ-2000
Adopted-2000
Standards-2000
Revised-0000
Revised-0000

FACTS publishes this document as a public service. Its use is voluntary, and all results obtained by its use must be entirely the responsibility of the user. This document is subject to revision, change and/or withdrawal at any time. © FACTS 2000

1.0 Purpose

- 1.1 This establishes the minimum standard for the glazing of artworks, keepsakes and the like.
- 1.2 This document is directed to only those areas that cannot be easily judged by visual examination of the product.

2.0 UV Blocking Glass or Acrylic

- 2.1 A glazing material shall block more than 50% of all UV light from 300 to 400 nanometers to be considered a UV Blocking glazing.
- 2.2 The higher the number, the greater the UV protection.

3.0 Anti-reflective Glass or Acrylic

- 3.1 A glazing material shall reduced reflection (or glare) to a refractive index of 7 or less and increased transmission (or clarity) compared to the base glass used (prior to the processing for anti-reflective surfaces).
- 3.2 The lower the number, the greater the anti-reflective qualities.